

SOIL GROUTING IMPROVER EXCELLENT IN SOLUTION HARDENING STABILITY AT LOW TEMPERATURE

Publication number: JP10036843 (A)

Publication date: 1998-02-10

Inventor(s): KITAMURA TADASHI; KUROKI HIDEKI

Applicant(s): MITSUI PETROCHEMICAL IND

Classification:

- **international:** *E02D3/12; C04B28/26; C09K17/42; C09K17/46; C09K17/48; E02D3/00; C04B28/00; C09K17/40; (IPC1-7): C09K17/46; C09K17/42; C09K17/48; E02D3/12; C09K103/00*

- **European:** C04B28/26

Application number: JP19960213144 19960724

Priority number(s): JP19960213144 19960724

Abstract of JP 10036843 (A)

PROBLEM TO BE SOLVED: To obtain a soil grouting improver excellent in soln. hardening stability at a low temp. which has excellent working stability by incorporating a curing agent, comprising phosphoric acid and glyoxal, and a chemical soln. stabilizer into a specified aq. sodium silicate soln. or a mixed aq. soln. contg. sodium silicate and colloidal silica. **SOLUTION:** An aq. soln. contg. sodium silicate having an SiO₂ to Na₂ O molar ratio of (2.45:1) to (4.5:1) in an amt. of 10 to 50wt.% in terms of the total amt. of SiO₂ and Na₂ O, or a mixed aq. soln. contg. sodium silicate having an SiO₂ to Na₂ O molar ratio of not more than (4.5:1) and a colloidal silica having an SiO₂ to Na₂ O molar ratio of (20:1) to (250:1), the SiO₂ to Na₂ O molar ratio in the aq. soln. being (3:1) to (50:1), the total amt. of SiO₂ and Na₂ O in the mixed aq. soln. being 10 to 50wt.%, is prepared as a main agent. An aq. curing agent soln. comprising phosphoric acid in an amt. capable of neutralizing 20 to 50mol% of Na₂ O in the main agent and glyoxal in an amt. capable of neutralizing 5 to 30mol% of Na₂ O in the main agent is then mixed with the main agent in a main agent to curing agent ratio of (1:0.9) to (0.9 to 1). This mixed soln. is then mixed with a chemical soln. stabilizer, such as urea or a urea compd., in an amt. of 0.1 to 10kg based on 200 liters of the chemical soln. to obtain a soil grouting improver.

Data supplied from the **esp@cenet** database — Worldwide